

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
20 March 2003 (20.03.2003)

PCT

(10) International Publication Number
WO 03/022807 A2(51) International Patent Classification⁷: C07D

(21) International Application Number: PCT/US02/28776

(22) International Filing Date:
10 September 2002 (10.09.2002)

(25) Filing Language: English

(26) Publication Language: English



(30) Priority Data:
09/950,307 10 September 2001 (10.09.2001) US
Not furnished 6 September 2002 (06.09.2002) US(71) Applicant (for all designated States except US): **ABBOTT LABORATORIES** [US/US]; D-377 AP6A-1, 100 Abbott Park Road, Abbott Park, IL 60064-6008 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **MOLLISON, Karl, W.** [US/US]; 4020 N Harvard Ave, Arlington Heights, IL 60004 (US). **LECAPTAIN, Angela, M.** [US/US]; 555 Bridlewood Ln, Oak Creek, WI 53154 (US). **BURKE, Sandra, E.** [US/US]; 1025 Regency Lane, Libertyville, IL60048 (US). **CROMACK, Keith, R.** [US/US]; 18066 W Banbury Dr, Gurnee, IL 60031 (US). **TARCHA, Peter, J.** [US/US]; 21651 Gelden Road, Lake Villa, IL 60046 (US). **CHEN, Yen-Chih, J.** [US/US]; 3315 Dartmouth Place, Evanston, IL 60201 (US).(74) Agents: **WEINSTEIN, David, L.** et al.; D-377 AP6A-1, 100 Abbott Park Road, Abbott Park, IL 60064-6008 (US).(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: MEDICAL DEVICES CONTAINING RAPAMYCIN ANALOGS



(57) **Abstract:** A medical device comprising a supporting structure capable of containing or supporting a pharmaceutically acceptable carrier or excipient, which carrier or excipient may contain one or more therapeutic agents or substances, with the carrier preferably including a coating on the surface thereof, and the coating containing the therapeutic substances, such as, for example, drugs. Supporting structures for the medical devices that are suitable for use in this invention include, but are not limited to, coronary stents, peripheral stents, catheters, arterio-venous grafts, by-pass grafts, and drug delivery balloons used in the vasculature. Drugs that are suitable for use in this invention include, but are not limited to Formula (I). This drug can be used in combination with another drug including those selected from anti-proliferative agents, anti-platelet agents, anti-inflammatory agents, anti-thrombotic agents, cytotoxic drugs, agents that inhibit cytokine or chemokine binding, cell de-differentiation inhibitors, anti-lipaedemic agents, matrix metalloproteinase inhibitors, cytostatic drugs, or combinations of these drugs.



WO 03/022807 A2



Published:

— without international search report and to be republished
upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

MEDICAL DEVICES CONTAINING RAPAMYCIN ANALOGS

This application is a continuation-in-part of United States Serial No. 09/950,307, filed September 10, 2001, which is a continuation-in-part of United States Serial No. 09/433,001, filed November 2, 1999, which is a divisional of United States Serial No. 09/159,945, filed September 24, 1998, now United States Patent No. 6,015,815, incorporated herein by reference.

Technical Field

The present invention relates to novel chemical compounds having immunomodulatory activity and synthetic intermediates useful for the preparation of the novel compounds, and in particular to macrolide immunomodulators. More particularly, the invention relates to semisynthetic analogs of rapamycin, means for their preparation, pharmaceutical compositions containing such compounds, and methods of treatment employing the same.


Background of The Invention

The compound cyclosporine (cyclosporin A) has found wide use since its introduction in the fields of organ transplantation and immunomodulation, and has brought about a significant increase in the success rate for transplantation procedures. Recently, several classes of macrocyclic compounds having potent immunomodulatory activity have been discovered. Okuhara *et al.*, in European Patent Application No. 184,162, published June 11, 1986, disclose a number of macrocyclic compounds isolated from the genus *Streptomyces*, including the immunosuppressant FK-506, a 23-membered macrocyclic lactone, which was isolated from a strain of *S. tsukubaensis*.

Other related natural products, such as FR-900520 and FR-900523, which differ from FK-506 in their alkyl substituent at C-21, have been isolated from *S. hygroscopicus yakushimnaensis*. Another analog, FR-900525, produced by *S. tsukubaensis*, differs from FK-506 in the replacement of a pipercolic acid moiety with a proline group. Unsatisfactory side-effects associated with cyclosporine and FK-506 such as nephrotoxicity, have led to a continued search for immunosuppressant compounds having improved efficacy and safety, including an immunosuppressive

agent which is effective topically, but ineffective systemically (U.S. Patent No. 5,457,111).

Rapamycin is a macrocyclic triene antibiotic produced by *Streptomyces hygroscopicus*, which was found to have antifungal activity, particularly against
 5 *Candida albicans*, both in vitro and in vivo (C. Vezina et al., *J. Antibiot.* 1975, 28, 721; S. N. Sehgal et al., *J. Antibiot.* 1975, 28, 727; H. A. Baker et al., *J. Antibiot.* 1978, 31, 539; U.S. Patent No. 3,929,992; and U.S. Patent No. 3,993,749).



Rapamycin

Rapamycin alone (U.S. Patent No. 4,885,171) or in combination with picibanil (U.S. Patent No. 4,401,653) has been shown to have antitumor activity. In 1977, rapamycin was also shown to be effective as an immunosuppressant in the experimental allergic encephalomyelitis model, a model for multiple sclerosis; in the
 15 adjuvant arthritis model, a model for rheumatoid arthritis; and was shown to effectively inhibit the formation of IgE-like antibodies (R. Martel et al., *Can. J. Physiol. Pharmacol.*, 1977, 55, 48).

The immunosuppressive effects of rapamycin have also been disclosed in *FASEB*, 1989, 3, 3411 as has its ability to prolong survival time of organ grafts in
 20 histoincompatible rodents (R. Morris, *Med. Sci. Res.*, 1989, 17, 877). The ability of rapamycin to inhibit T-cell activation was disclosed by M. Strauch (*FASEB*, 1989, 3, 3411). These and other biological effects of rapamycin are reviewed in *Transplantation Reviews*, 1992, 6, 39-87.

Rapamycin has been shown to reduce neointimal proliferation in animal
 25 models, and to reduce the rate of restenosis in humans. Evidence has been

published showing that rapamycin also exhibits an anti-inflammatory effect, a characteristic which supported its selection as an agent for the treatment of rheumatoid arthritis. Because both cell proliferation and inflammation are thought to be causative factors in the formation of restenotic lesions after balloon angioplasty and stent placement, rapamycin and analogs thereof have been proposed for the prevention of restenosis.

Mono-ester and di-ester derivatives of rapamycin (esterification at positions 31 and 42) have been shown to be useful as antifungal agents (U.S. Patent No. 4,316,885) and as water soluble prodrugs of rapamycin (U.S. Patent No. 4,650,803).

Fermentation and purification of rapamycin and 30-demethoxy rapamycin have been described in the literature (C. Vezina et al. *J. Antibiot.* (Tokyo), 1975, 28(10), 721; S. N. Sehgal et al., *J. Antibiot.* (Tokyo), 1975, 28(10), 727; 1983, 36(4), 351; N. L. Pavia et al., *J. Natural Products*, 1991, 54(1), 167-177).

Numerous chemical modifications of rapamycin have been attempted. These include the preparation of mono- and di-ester derivatives of rapamycin (WO 92/05179), 27-oximes of rapamycin (EP0 467606); 42-oxo analog of rapamycin (U.S. Patent No. 5,023,262); bicyclic rapamycins (U.S. Patent No. 5,120,725); rapamycin dimers (U.S. Patent No. 5,120,727); silyl ethers of rapamycin (U.S. Patent No. 5,120,842); and arylsulfonates and sulfamates (U.S. Patent No. 5,177, 203). Rapamycin was recently synthesized in its naturally occurring enantiomeric form (K. C. Nicolaou et al., *J. Am. Chem. Soc.*, 1993, 115, 4419-4420; S. L. Schreiber, *J. Am. Chem. Soc.*, 1993, 115, 7906-7907; S. J. Danishefsky, *J. Am. Chem. Soc.*, 1993, 115, 9345-9346).

It has been known that rapamycin, like FK-506, binds to FKBP-12 (Siekierka, J. J.; Hung, S. H. Y.; Poe, M.; Lin, C. S.; Sigal, N. H. *Nature*, **1989**, 341, 755-757; Harding, M. W.; Galat, A.; Uehling, D. E.; Schreiber, S. L. *Nature* **1989**, 341, 758-760; Dumont, F. J.; Melino, M. R.; Staruch, M. J.; Koprak, S. L.; Fischer, P. A.; Sigal, N. H. *J. Immunol.* **1990**, 144, 1418-1424; Bierer, B. E.; Schreiber, S. L.; Burakoff, S. J. *Eur. J. Immunol.* **1991**, 21, 439-445; Fretz, H.; Albers, M. W.; Galat, A.; Standaert, R. F.; Lane, W. S.; Burakoff, S. J.; Bierer, B. E.; Schreiber, S. L. *J. Am. Chem. Soc.* **1991**, 113, 1409-1411). Recently it has been discovered that the rapamycin/FKBP-12 complex binds to yet another protein, which is distinct from calcineurin, the protein that the FK-506/FKBP-12 complex inhibits (Brown, E. J.; Albers, M. W.; Shin,

T. B.; Ichikawa, K.; Keith, C. T.; Lane, W. S.; Schreiber, S. L. *Nature* **1994**, 369, 756-758; Sabatini, D. M.; Erdjument-Bromage, H.; Lui, M.; Tempest, P.; Snyder, S. H. *Cell*, **1994**, 78, 35-43).

Percutaneous transluminal coronary angioplasty (PTCA) was developed by Andreas Gruntzig in the 1970's. The first canine coronary dilation was performed on September 24, 1975; studies showing the use of PTCA were presented at the annual meetings of the American Heart Association the following year. Shortly thereafter, the first human patient was studied in Zurich, Switzerland, followed by the first American human patients in San Francisco and New York. While this procedure changed the practice of interventional cardiology with respect to treatment of patients with obstructive coronary artery disease, the procedure did not provide long-term solutions. Patients received only temporary abatement of the chest pain associated with vascular occlusion; repeat procedures were often necessary. It was determined that the existence of restenotic lesions severely limited the usefulness of the new procedure. In the late 1980's, stents were introduced to maintain vessel patency after angioplasty. Stenting is involved in 90% of angioplasty performed today. Before the introduction of stents, the rate of restenosis ranged from 30% to 50% of the patients who were treated with balloon angioplasty. The recurrence rate after dilatation of in-stent restenosis may be as high as 70% in selected patient subsets, while the angiographic restenosis rate in de novo stent placement is about 20%. Placement of the stent reduced the restenosis rate to 15% to 20%. This percentage likely represents the best results obtainable with purely mechanical stenting. The restenosis lesion is caused primarily by neointimal hyperplasia, which is distinctly different from atherosclerotic disease both in time-course and in histopathologic appearance. Restenosis is a healing process of damaged coronary arterial walls, with neointimal tissue impinging significantly on the vessel lumen. Vascular brachytherapy appears to be efficacious against in-stent restenosis lesions. Radiation, however, has limitations of practicality and expense, and lingering questions about safety and durability.

Accordingly, it is desired to reduce the rate of restenosis by at least 50% of its current level. It is for this reason that a major effort is underway by the interventional device community to fabricate and evaluate drug-eluting stents. Such devices could have many advantages if they were successful, principally since such systems would

need no auxiliary therapies, either in the form of peri-procedural techniques or chronic oral pharmacotherapy.

Brief Description of the Drawings

Figure 1 shows blood concentrations \pm SEM (n=3) of tetrazole-containing rapamycin analogs dosed in monkey.


Figure 2 is a side view in elevation showing a stent suitable for use in this invention.

Figure 3A is a cross-sectional view of a vessel segment in which was placed a stent coated with a polymer only.

Figure 3B is a cross-sectional view of a vessel segment in which was placed a stent coated with a polymer plus drug.

Summary of the Invention

In one aspect of the present invention are disclosed compounds represented by the structural formula:




or a pharmaceutically acceptable salt or prodrug thereof.

Another object of the present invention is to provide synthetic processes for the preparation of such compounds from starting materials obtained by fermentation, as well as chemical intermediates useful in such synthetic processes.


A further object of the invention is to provide pharmaceutical compositions containing, as an active ingredient, at least one of the above compounds.

Yet another object of the invention is to provide a method of treating a variety of disease states, including restenosis, post-transplant tissue rejection, immune and autoimmune dysfunction, fungal growth, and cancer.

In another aspect this invention provides a medical device comprising a supporting structure having a coating on the surface thereof, the coating containing a therapeutic substance, such as, for example, a drug. Supporting structures for the medical devices that are suitable for use in this invention include, but are not limited to, coronary stents, peripheral stents, catheters, arterio-venous grafts, by-pass grafts, and drug delivery balloons used in the vasculature. Drugs that are suitable for use in this invention include, but are not limited to,




or a pharmaceutically acceptable salt or prodrug thereof, which includes




or a pharmaceutically acceptable salt or prodrug thereof, (hereinafter alternatively referred to as A-179578), and

5




or a pharmaceutically acceptable salt or prodrug thereof;



or a pharmaceutically acceptable salt or prodrug thereof, (hereinafter alternatively referred to as SDZ RAD or 40-O-(2-hydroxyethyl)-rapamycin);

5



or a pharmaceutically acceptable salt or prodrug thereof, (hereinafter alternatively referred to as A-94507).

10

Coatings that are suitable for use in this invention include, but are not limited to, polymeric coatings that can comprise any polymeric material in which the therapeutic agent, i.e., the drug, is substantially soluble. The coating can be hydrophilic, hydrophobic, biodegradable, or non-biodegradable. This medical device reduces restenosis in vasculature. The direct coronary delivery of a drug such as A-

15

179578 is expected to reduce the rate of restenosis to a level of about 0% to 25%.

Detailed Description of the Invention

Definition of Terms

5 The term "prodrug," as used herein, refers to compounds which are rapidly transformed in vivo to the parent compound of the above formula, for example, by hydrolysis in blood. A thorough discussion is provided by T. Higuchi and V. Stella, "Pro-drugs as Novel Delivery systems," Vol. 14 of the A. C. S. Symposium Series, and in Edward B. Roche, ed., "Bioreversible Carriers in Drug Design," American
10 Pharmaceutical Association and Pergamon Press, 1987, both of which are incorporated herein by reference.


 The term "pharmaceutically acceptable prodrugs", as used herein, refers to those prodrugs of the compounds of the present invention which are, within the scope of sound medical judgment, suitable for use in contact with the tissues of
15 humans and lower mammals without undue toxicity, irritation, and allergic response, are commensurate with a reasonable benefit/risk ratio, and are effective for their intended use, as well as the zwitterionic forms, where possible, of the compounds of the invention. Particularly preferred pharmaceutically acceptable prodrugs of this invention are prodrug esters of the C-31 hydroxyl group of compounds of this
20 invention.

 The term "prodrug esters," as used herein, refers to any of several ester-forming groups that are hydrolyzed under physiological conditions. Examples of prodrug ester groups include acetyl, ethanoyl, pivaloyl, pivaloyloxymethyl, acetoxymethyl, phthalidyl, methoxymethyl, indanyl, and the like, as well as ester
25 groups derived from the coupling of naturally or unnaturally-occurring amino acids to the C-31 hydroxyl group of compounds of this invention.

 The term "supporting structure" means a framework that is capable of containing or supporting a pharmaceutically acceptable carrier or excipient, which carrier or excipient may contain one or more therapeutic agents or substances, e.g.,
30 one or more drugs and/or other compounds. The supporting structure is typically formed of metal or a polymeric material. Suitable supporting structures formed of polymeric materials, including biodegradable polymers, capable of containing the therapeutic agents or substances include, without limitation, those disclosed in U.S. Patent Nos. 6,413,272 and 5,527,337, which are incorporated herein by reference.


Embodiments

In one embodiment of the invention is a compound of formula



5

In another embodiment of the invention is a compound of formula



10



Preparation of Compounds of this Invention

The compounds and processes of the present invention will be better understood in connection with the following synthetic schemes which illustrate the methods by which the compounds of the invention may be prepared.


The compounds of this invention may be prepared by a variety of synthetic routes. A representative procedure is shown in Scheme 1.

15

Scheme 1



A



epimeric mixture (B/C)

As shown in Scheme 1, conversion of the C-42 hydroxyl of rapamycin to a trifluoromethanesulfonate or fluorosulfonate leaving group provided A. Displacement

of the leaving group with tetrazole in the presence of a hindered, non-nucleophilic base, such as 2,6-lutidine, or, preferably, diisopropylethyl amine provided epimers B and C, which were separated and purified by flash column chromatography.

5

Synthetic Methods

The foregoing may be better understood by reference to the following examples which illustrate the methods by which the compounds of the invention may be prepared and are not intended to limit the scope of the invention as defined in the appended claims.

10

Example 1

42-Epi-(tetrazolyl)-rapamycin (less polar isomer)

Example 1A

A solution of rapamycin (100 mg, 0.11 mmol) in dichloromethane (0.6 mL) at -
15 78 °C under a nitrogen atmosphere was treated sequentially with 2,6-lutidine (53 uL, 0.46 mmol, 4.3 eq.) and trifluoromethanesulfonic anhydride (37 uL, 0.22 mmol), and stirred thereafter for 15 minutes, warmed to room temperature and eluted through a pad of silica gel (6 mL) with diethyl ether. Fractions containing the triflate were pooled and concentrated to provide the designated compound as an amber foam.

20

Example 1B

42-Epi-(tetrazolyl)-rapamycin (less polar isomer)

A solution of Example 1A in isopropyl acetate (0.3 mL) was treated sequentially with diisopropylethylamine (87 mL, 0.5 mmol) and 1H-tetrazole (35 mg, 0.5 mmol), and thereafter stirred for 18 hours. This mixture was partitioned between
25 water (10 mL) and ether (10 mL). The organics were washed with brine (10 mL) and dried (Na₂SO₄). Concentration of the organics provided a sticky yellow solid which was purified by chromatography on silica gel (3.5 g, 70-230 mesh) eluting with hexane (10 mL), hexane:ether (4:1(10 mL), 3:1(10 mL), 2:1(10 mL), 1:1(10 mL)),
30 ether (30 mL), hexane:acetone (1:1(30mL)). One of the isomers was collected in the ether fractions.

MS (ESI) m/e 966 (M)⁻;

Example 242-Epi-(tetrazolyl)-rapamycin (more polar isomer)Example 2A42-Epi-(tetrazolyl)-rapamycin (more polar isomer)

Collection of the slower moving band from the chromatography column using the hexane:acetone (1:1) mobile phase in Example 1B provided the designated compound.

MS (ESI) m/e 966 (M)⁻.

In vitro Assay of Biological Activity

The immunosuppressant activity of the compounds of the present invention was compared to rapamycin and two rapamycin analogs: 40-epi-N-[2'-pyridone]-rapamycin and 40-epi-N-[4'-pyridone]-rapamycin, both disclosed in U. S. Patent No. 5,527,907. The activity was determined using the human mixed lymphocyte reaction (MLR) assay described by Kino, T. *et al.* in *Transplantation Proceedings*, XIX(5):36-39, Suppl. 6 (1987). The results of the assay demonstrate that the compounds of the invention are effective immunomodulators at nanomolar concentrations, as shown in Table 1.

Table 1

Example	Human MLR IC ₅₀ ± S.E.M.(nM)
Rapamycin	0.91 ± 0.36
2-pyridone	12.39 ± 5.3
4-pyridone	0.43 ± 0.20
Example 1	1.70 ± 0.48
Example 2	0.66 ± 0.19

The pharmacokinetic behaviors of Example 1 and Example 2 were characterized following a single 2.5 mg/kg intravenous dose in cynomolgus monkey (n=3 per group). Each compound was prepared as 2.5 mg/mL solution in a 20% ethanol:30% propylene glycol:2% cremophor EL:48% dextrose 5% in water vehicle.

The 1 mL/kg intravenous dose was administered as a slow bolus (~1-2 minutes) in a saphenous vein of the monkeys. Blood samples were obtained from a femoral artery or vein of each animal prior to dosing and 0.1 (IV only), 0.25, 0.5, 1, 1.5, 2, 4, 6, 9, 12, 24, and 30 hours after dosing. The EDTA preserved samples were thoroughly
5 mixed and extracted for subsequent analysis.

An aliquot of blood (1.0 mL) was hemolyzed with 20% methanol in water (0.5 ml) containing an internal standard. The hemolyzed samples were extracted with a mixture of ethyl acetate and hexane (1:1 (v/v), 6.0 mL). The organic layer was evaporated to dryness with a stream of nitrogen at room temperature. Samples
10 were reconstituted in methanol: water (1:1, 150 μ L). The title compounds (50 μ L injection) were separated from contaminants using reverse phase HPLC with UV detection. Samples were kept cool (4 °C) through the run. All samples from each study were analyzed as a single batch on the HPLC.

Area under the curve (AUC) measurements of Example 1, Example 2 and the
15 internal standard were determined using the Sciex MacQuan™ software. Calibration curves were derived from peak area ratio (parent drug/internal standard) of the spiked blood standards using least squares linear regression of the ratio versus the theoretical concentration. The methods were linear for both compounds over the range of the standard curve (correlation > 0.99) with an estimated quantitation limit
20 of 0.1 ng/mL. The maximum blood concentration (C_{MAX}) and the time to reach the maximum blood concentration (T_{MAX}) were read directly from the observed blood concentration-time data. The blood concentration data were submitted to multi-exponential curve fitting using CSTRIP to obtain estimates of pharmacokinetic parameters. The estimated parameters were further defined using NONLIN84. The
25 area under the blood concentration-time curve from 0 to t hours (last measurable blood concentration time point) after dosing (AUC_{0-t}) was calculated using the linear trapezoidal rule for the blood-time profiles. The residual area extrapolated to infinity, determined as the final measured blood concentration (C_t) divided by the terminal elimination rate constant (β), and added to AUC_{0-t} to produce the total area under the
30 curve ($AUC_{0-\infty}$).

As shown in Figure 1 and Table 2, both Example 1 and Example 2 had a surprisingly substantially shorter terminal elimination half-life ($t_{1/2}$) when compared to rapamycin. Thus, only the compounds of the invention provide both sufficient efficacy (Table 1) and a shorter terminal half-life (Table 2).

Table 2

Compound	AUC ng·hr/mL	t _{1/2} (hours)
Rapamycin	6.87	16.7
2-pyridone	2.55	2.8
4-pyridone	5.59	13.3
Example 1	2.35	5.0
Example 2	2.38	6.9

5 Methods of Treatment

The compounds of the invention, including but not limited to those specified in the examples, possess immunomodulatory activity in mammals (especially humans). As immunosuppressants, the compounds of the present invention are useful for the treatment and prevention of immune-mediated diseases such as the resistance by

10 transplantation of organs or tissue such as heart, kidney, liver, medulla ossium, skin, cornea, lung, pancreas, intestinum tenue, limb, muscle, nerves, duodenum, small-bowel, pancreatic-islet-cell, and the like; graft-versus-host diseases brought about by medulla ossium transplantation; autoimmune diseases such as rheumatoid arthritis, systemic lupus erythematosus, Hashimoto's thyroiditis, multiple sclerosis,

15 myasthenia gravis, type I diabetes, uveitis, allergic encephalomyelitis, glomerulonephritis, and the like. Further uses include the treatment and prophylaxis of inflammatory and hyperproliferative skin diseases and cutaneous manifestations of immunologically-mediated illnesses, such as psoriasis, atopic dermatitis, contact dermatitis and further eczematous dermatitises, seborrhoeis dermatitis, lichen

20 planus, pemphigus, bullous pemphigoid, epidermolysis bullosa, urticaria, angioedemas, vasculitides, erythemas, cutaneous eosinophilias, lupus erythematosus, acne and alopecia areata; various eye diseases (autoimmune and otherwise) such as keratoconjunctivitis, vernal conjunctivitis, uveitis associated with Behcet's disease, keratitis, herpetic keratitis, conical cornea, dystrophia epithelialis

25 corneae, corneal leukoma, and ocular pemphigus. In addition reversible obstructive airway disease, which includes conditions such as asthma (for example, bronchial asthma, allergic asthma, intrinsic asthma, extrinsic asthma and dust asthma),

particularly chronic or inveterate asthma (for example, late asthma and airway hyper-responsiveness), bronchitis, allergic rhinitis, and the like are targeted by compounds of this invention. Inflammation of mucosa and blood vessels such as gastric ulcers, vascular damage caused by ischemic diseases and thrombosis. Moreover,
5 hyperproliferative vascular diseases such as intimal smooth muscle cell hyperplasia, restenosis and vascular occlusion, particularly following biologically- or mechanically-mediated vascular injury, could be treated or prevented by the compounds of the invention.

The compounds or drugs described herein can be applied to stents that have
10 been coated with a polymeric compound. Incorporation of the compound or drug into the polymeric coating of the stent can be carried out by dipping the polymer-coated stent into a solution containing the compound or drug for a sufficient period of time (such as, for example, five minutes) and then drying the coated stent, preferably by means of air drying for a sufficient period of time (such as, for example, 30
15 minutes). The polymer-coated stent containing the compound or drug can then be delivered to the coronary vessel by deployment from a balloon catheter. In addition to stents, other devices that can be used to introduce the drugs of this invention to the vasculature include, but are not limited to grafts, catheters, and balloons. In addition, other compounds or drugs that can be used in lieu of the drugs of this
20 invention include, but are not limited to, A-94507 and SDZ RAD).

The compounds described herein for use in polymer-coated stents can be used in combination with other pharmacological agents. The pharmacological agents that would, in combination with the compounds of this invention, be most effective in preventing restenosis can be classified into the categories of anti-
25 proliferative agents, anti-platelet agents, anti-inflammatory agents, anti-thrombotic agents, and thrombolytic agents. These classes can be further sub-divided. For example, anti-proliferative agents can be anti-mitotic. Anti-mitotic agents inhibit or affect cell division, whereby processes normally involved in cell division do not take place. One sub-class of anti-mitotic agents includes vinca alkaloids. Representative
30 examples of vinca alkaloids include, but are not limited to, vincristine, paclitaxel, etoposide, nocodazole, indirubin, and anthracycline derivatives, such as, for example, daunorubicin, daunomycin, and plicamycin. Other sub-classes of anti-mitotic agents include anti-mitotic alkylating agents, such as, for example, tauromustine, bofumustine, and fotemustine, and anti-mitotic metabolites, such as,

for example, methotrexate, fluorouracil, 5-bromodeoxyuridine, 6-azacytidine, and cytarabine. Anti-mitotic alkylating agents affect cell division by covalently modifying DNA, RNA, or proteins, thereby inhibiting DNA replication, RNA transcription, RNA translation, protein synthesis, or combinations of the foregoing.

5 Anti-platelet agents are therapeutic entities that act by (1) inhibiting adhesion of platelets to a surface, typically a thrombogenic surface, (2) inhibiting aggregation of platelets, (3) inhibiting activation of platelets, or (4) combinations of the foregoing. Activation of platelets is a process whereby platelets are converted from a quiescent, resting state to one in which platelets undergo a number of morphologic changes
10 induced by contact with a thrombogenic surface. These changes include changes in the shape of the platelets, accompanied by the formation of pseudopods, binding to membrane receptors, and secretion of small molecules and proteins, such as, for example, ADP and platelet factor 4. Anti-platelet agents that act as inhibitors of adhesion of platelets include, but are not limited to, eptifibatide, tirofiban, RGD (Arg-
15 Gly-Asp)-based peptides that inhibit binding to gpIIbIIIa or $\alpha v\beta 3$, antibodies that block binding to gpIIaIIIb or $\alpha v\beta 3$, anti-P-selectin antibodies, anti-E-selectin antibodies, peptides that block P-selectin or E-selectin binding to their respective ligands, saratin, and anti-von Willebrand factor antibodies. Agents that inhibit ADP-mediated platelet aggregation include, but are not limited to, disagregin and
20 cilostazol.

 Anti-inflammatory agents can also be used. Examples of these include, but are not limited to, prednisone, dexamethasone, hydrocortisone, estradiol, and non-steroidal anti-inflammatories, such as, for example, acetaminophen, ibuprofen, naproxen, and sulindac. Other examples of these agents include those that inhibit
25 binding of cytokines or chemokines to the cognate receptors to inhibit pro-inflammatory signals transduced by the cytokines or the chemokines. Representative examples of these agents include, but are not limited to, anti-IL1, anti-IL2, anti-IL3, anti-IL4, anti-IL8, anti-IL15, anti-GM-CSF, and anti-TNF antibodies.

 Anti-thrombotic agents include chemical and biological entities that can
30 intervene at any stage in the coagulation pathway. Examples of specific entities include, but are not limited to, small molecules that inhibit the activity of factor Xa. In addition, heparinoid-type agents that can inhibit both FXa and thrombin, either directly or indirectly, such as, for example, heparin, heparan sulfate, low molecular weight heparins, such as, for example, the compound having the trademark

Clivarin®, and synthetic oligosaccharides, such as, for example, the compound having the trademark Arixtra®. Also included are direct thrombin inhibitors, such as, for example, melagatran, ximelagatran, argatroban, inogatran, and peptidomimetics of binding site of the Phe-Pro-Arg fibrinogen substrate for thrombin. Another class of
5 anti-thrombotic agents that can be delivered are factor VII/VIIa inhibitors, such as, for example, anti-factor VII/VIIa antibodies, rNAPc2, and tissue factor pathway inhibitor (TFPI).

Thrombolytic agents, which may be defined as agents that help degrade thrombi (clots), can also be used as adjunctive agents, because the action of lysing a
10 clot helps to disperse platelets trapped within the fibrin matrix of a thrombus. Representative examples of thrombolytic agents include, but are not limited to, urokinase or recombinant urokinase, pro-urokinase or recombinant pro-urokinase, tissue plasminogen activator or its recombinant form, and streptokinase.

Other drugs that can be used in combination with the compounds of this
15 invention are cytotoxic drugs, such as, for example, apoptosis inducers, such as TGF, and topoisomerase inhibitors, such as, 10-hydroxycamptothecin, irinotecan, and doxorubicin. Other classes of drugs that can be used in combination with the compounds of this invention are drugs that inhibit cell de-differentiation and cytostatic drugs.

20 Other agents that can be used in combination with the compounds of this invention include anti-lipaedemic agents, such as, for example, fenofibrate, matrix metalloproteinase inhibitors, such as, for example, batimistat, antagonists of the endothelin-A receptor, such as, for example, darusentan, and antagonists of the $\alpha v \beta 3$ integrin receptor.

25 When used in the present invention, the coating can comprise any polymeric material in which the therapeutic agent, i.e., the drug, is substantially soluble. The purpose of the coating is to serve as a controlled release vehicle for the therapeutic agent or as a reservoir for a therapeutic agent to be delivered at the site of a lesion. The coating can be polymeric and can further be hydrophilic, hydrophobic,
30 biodegradable, or non-biodegradable. The material for the polymeric coating can be selected from the group consisting of polycarboxylic acids, cellulosic polymers, gelatin, polyvinylpyrrolidone, maleic anhydride polymers, polyamides, polyvinyl alcohols, polyethylene oxides, glycosaminoglycans, polysaccharides, polyesters, polyurethanes, silicones, polyorthoesters, polyanhydrides, polycarbonates,

polypropylenes, polylactic acids, polyglycolic acids, polycaprolactones, polyhydroxybutyrate valerates, polyacrylamides, polyethers, and mixtures and copolymers of the foregoing. Coatings prepared from polymeric dispersions such as polyurethane dispersions (BAYHYDROL, etc.) and acrylic acid latex dispersions can also be used with the therapeutic agents of the present invention.

Biodegradable polymers that can be used in this invention include polymers such as poly(L-lactic acid), poly(DL-lactic acid), polycaprolactone, poly(hydroxy butyrate), polyglycolide, poly(di- ϵ -clonine), poly(hydroxy valerate), polyorthoester; copolymers such as poly (lactide-co-glycolide), polyhydroxy (butyrate-co-valerate), polyglycolide-co-trimethylene carbonate; polyanhydrides; polyphosphoester; polyphosphoester-urethane; polyamino acids; polycyanoacrylates; biomolecules such as fibrin, fibrinogen, cellulose, starch, collagen and hyaluronic acid; and mixtures of the foregoing. Biostable materials that are suitable for use in this invention include polymers such as polyurethane, silicones, polyesters, polyolefins, polyamides, polycaprolactam, polyimide, polyvinyl chloride, polyvinyl methyl ether, polyvinyl alcohol, acrylic polymers and copolymers, polyacrylonitrile, polystyrene copolymers of vinyl monomers with olefins (such as styrene acrylonitrile copolymers, ethylene methyl methacrylate copolymers, ethylene vinyl acetate), polyethers, rayons, cellulose (such as cellulose acetate, cellulose nitrate, cellulose propionate, etc.), parylene and derivatives thereof; and mixtures and copolymers of the foregoing.

Another polymer that can be used in this invention is poly(MPC_w:LAM_x:HPMA_y:TSMA_z) where w, x, y, and z represent the molar ratios of monomers used in the feed for preparing the polymer and MPC represents the unit 2-methacryoyloxyethylphosphorylcholine, LMA represents the unit lauryl methacrylate, HPMA represents the unit 2-hydroxypropyl methacrylate, and TSMA represents the unit 3-trimethoxysilylpropyl methacrylate. The drug-impregnated stent can be used to maintain patency of a coronary artery previously occluded by thrombus and/or atherosclerotic plaque. The delivery of an anti-proliferative agent reduces the rate of in-stent restenosis.

Other treatable conditions include but are not limited to ischemic bowel diseases, inflammatory bowel diseases, necrotizing enterocolitis, intestinal inflammations/allergies such as Coeliac diseases, proctitis, eosinophilic gastroenteritis, mastocytosis, Crohn's disease and ulcerative colitis; nervous

diseases such as multiple myositis, Guillain-Barre syndrome, Meniere's disease, polyneuritis, multiple neuritis, mononeuritis and radiculopathy; endocrine diseases such as hyperthyroidism and Basedow's disease; hematic diseases such as pure red cell aplasia, aplastic anemia, hypoplastic anemia, idiopathic thrombocytopenic purpura, autoimmune hemolytic anemia, agranulocytosis, pernicious anemia, megaloblastic anemia and anerythroplasia; bone diseases such as osteoporosis; respiratory diseases such as sarcoidosis, fibroid lung and idiopathic interstitial pneumonia; skin disease such as dermatomyositis, leukoderma vulgaris, ichthyosis vulgaris, photoallergic sensitivity and cutaneous T cell lymphoma; circulatory diseases such as arteriosclerosis, atherosclerosis, aortitis syndrome, polyarteritis nodosa and myocardosis; collagen diseases such as scleroderma, Wegener's granuloma and Sjogren's syndrome; adiposis; eosinophilic fasciitis; periodontal disease such as lesions of gingiva, periodontium, alveolar bone and substantia ossea dentis; nephrotic syndrome such as glomerulonephritis; male pattern alopecia or alopecia senilis by preventing epilation or providing hair germination and/or promoting hair generation and hair growth; muscular dystrophy; Pyoderma and Sezary's syndrome; Addison's disease; active oxygen-mediated diseases, as for example organ injury such as ischemia-reperfusion injury of organs (such as heart, liver, kidney and digestive tract) which occurs upon preservation, transplantation or ischemic disease (for example, thrombosis and cardiac infarction); intestinal diseases such as endotoxin-shock, pseudomembranous colitis and colitis caused by drug or radiation; renal diseases such as ischemic acute renal insufficiency and chronic renal insufficiency; pulmonary diseases such as toxinosis caused by lung-oxygen or drug (for example, paracort and bleomycins), lung cancer and pulmonary emphysema; ocular diseases such as cataracta, siderosis, retinitis, pigmentosa, senile macular degeneration, vitreal scarring and corneal alkali burn; dermatitis such as erythema multiforme, linear IgA ballous dermatitis and cement dermatitis; and others such as gingivitis, periodontitis, sepsis, pancreatitis, diseases caused by environmental pollution (for example, air pollution), aging, carcinogenesis, metastasis of carcinoma and hypobaropathy; diseases caused by histamine or leukotriene-C₄ release; Behcet's disease such as intestinal-, vasculo- or neuro-Behcet's disease, and also Behcet's which affects the oral cavity, skin, eye, vulva, articulation, epididymis, lung, kidney and so on. Furthermore, the compounds of the invention are useful for the treatment and prevention of hepatic disease such as

immunogenic diseases (for example, chronic autoimmune liver diseases such as autoimmune hepatitis, primary biliary cirrhosis and sclerosing cholangitis), partial liver resection, acute liver necrosis (e.g. necrosis caused by toxin, viral hepatitis, shock or anoxia), B-virus hepatitis, non-A/non-B hepatitis, cirrhosis (such as
5 alcoholic cirrhosis) and hepatic failure such as fulminant hepatic failure, late-onset hepatic failure and "acute-on-chronic" liver failure (acute liver failure on chronic liver diseases), and moreover are useful for various diseases because of their useful activity such as augmentation of chemotherapeutic effect, cytomegalovirus infection, particularly HCMV infection, anti-inflammatory activity, sclerosing and fibrotic
10 diseases such as nephrosis, scleroderma, pulmonary fibrosis, arteriosclerosis, congestive heart failure, ventricular hypertrophy, post-surgical adhesions and scarring, stroke, myocardial infarction and injury associated with ischemia and reperfusion, and the like.

Additionally, compounds of the invention possess FK-506 antagonistic
15 properties. The compounds of the present invention may thus be used in the treatment of immunodepression or a disorder involving immunodepression. Examples of disorders involving immunodepression include AIDS, cancer, fungal infections, senile dementia, trauma (including wound healing, surgery and shock) chronic bacterial infection, and certain central nervous system disorders. The
20 immunodepression to be treated may be caused by an overdose of an immunosuppressive macrocyclic compound, for example derivatives of 12-(2-cyclohexyl-1-methylvinyl)-13, 19,21,27-tetramethyl-11,28-dioxa-4-azatricyclo[22.3.1.0^{4,9}] octacos-18-ene such as FK-506 or rapamycin. The overdosing of such medicaments by patients is quite common upon their realizing
25 that they have forgotten to take their medication at the prescribed time and can lead to serious side effects.

The ability of the compounds of the invention to treat proliferative diseases can be demonstrated according to the methods described in Bunchman ET and CA Brookshire, Transplantation Proceed. 23 967-968 (1991); Yamagishi, et al.,
30 Biochem. Biophys. Res. Comm. 191 840-846 (1993); and Shichiri, et al., J. Clin. Invest. 87 1867-1871 (1991). Proliferative diseases include smooth muscle proliferation, systemic sclerosis, cirrhosis of the liver, adult respiratory distress syndrome, idiopathic cardiomyopathy, lupus erythematosus, diabetic retinopathy or other retinopathies, psoriasis, scleroderma, prostatic hyperplasia, cardiac

hyperplasia, restenosis following arterial injury or other pathologic stenosis of blood vessels. In addition, these compounds antagonize cellular responses to several growth factors, and therefore possess antiangiogenic properties, making them useful agents to control or reverse the growth of certain tumors, as well as fibrotic diseases of the lung, liver, and kidney.

Aqueous liquid compositions of the present invention are particularly useful for the treatment and prevention of various diseases of the eye such as autoimmune diseases (including, for example, conical cornea, keratitis, dysopia epithelialis corneae, leukoma, Mooren's ulcer, scleritis and Graves' ophthalmopathy) and rejection of corneal transplantation.

When used in the above or other treatments, a therapeutically effective amount of one of the compounds of the present invention may be employed in pure form or, where such forms exist, in pharmaceutically acceptable salt, ester or prodrug form. Alternatively, the compound may be administered as a pharmaceutical composition containing the compound of interest in combination with one or more pharmaceutically acceptable excipients. The phrase "therapeutically effective amount" of the compound of the invention means a sufficient amount of the compound to treat disorders, at a reasonable benefit/risk ratio applicable to any medical treatment. It will be understood, however, that the total daily usage of the compounds and compositions of the present invention will be decided by the attending physician within the scope of sound medical judgment. The specific therapeutically effective dose level for any particular patient will depend upon a variety of factors including the disorder being treated and the severity of the disorder; activity of the specific compound employed; the specific composition employed; the age, body weight, general health, sex and diet of the patient; the time of administration, route of administration, and rate of excretion of the specific compound employed; the duration of the treatment; drugs used in combination or coincidental with the specific compound employed; and like factors well known in the medical arts. For example, it is well within the skill of the art to start doses of the compound at levels lower than required to achieve the desired therapeutic effect and to gradually increase the dosage until the desired effect is achieved.

The total daily dose of the compounds of this invention administered to a human or lower animal may range from about 0.01 to about 10 mg/kg/day. For purposes of oral administration, more preferable doses may be in the range of from

about 0.001 to about 3 mg/kg/day. For the purposes of local delivery from a stent, the daily dose that a patient will receive depends on the length of the stent. For example, a 15 mm coronary stent may contain a drug in an amount ranging from about 1 to about 120 micrograms and may deliver that drug over a time period
5 ranging from several hours to several weeks. If desired, the effective daily dose may be divided into multiple doses for purposes of administration; consequently, single dose compositions may contain such amounts or submultiples thereof to make up the daily dose. Topical administration may involve doses ranging from 0.001 to 3% mg/kg/day, depending on the site of application.

10

Pharmaceutical Compositions

The pharmaceutical compositions of the present invention comprise a compound of the invention and a pharmaceutically acceptable carrier or excipient, which may be administered orally, rectally, parenterally, intracisternally,
15 intravaginally, intraperitoneally, topically (as by powders, ointments, drops or transdermal patch), buccally, as an oral or nasal spray, or locally, as in a stent placed within the vasculature. The phrase "pharmaceutically acceptable carrier" means a non-toxic solid, semi-solid or liquid filler, diluent, encapsulating material or formulation auxiliary of any type. The term "parenteral," as used herein, refers to
20 modes of administration which include intravenous, intraarterial, intramuscular, intraperitoneal, intrasternal, subcutaneous and intraarticular injection, infusion, and placement, such as , for example, in vasculature.

Pharmaceutical compositions of this invention for parenteral injection comprise pharmaceutically acceptable sterile aqueous or nonaqueous solutions,
25 dispersions, suspensions or emulsions as well as sterile powders for reconstitution into sterile injectable solutions or dispersions just prior to use. Examples of suitable aqueous and nonaqueous carriers, diluents, solvents or vehicles include water, ethanol, polyols (such as glycerol, propylene glycol, polyethylene glycol, and the like), carboxymethylcellulose and suitable mixtures thereof, vegetable oils (such as
30 olive oil), and injectable organic esters such as ethyl oleate. Proper fluidity can be maintained, for example, by the use of coating materials such as lecithin, by the maintenance of the required particle size in the case of dispersions, and by the use of surfactants.

These compositions may also contain adjuvants such as preservatives, wetting agents, emulsifying agents, and dispersing agents. Prevention of the action of microorganisms may be ensured by the inclusion of various antibacterial and antifungal agents, for example, paraben, chlorobutanol, phenol sorbic acid, and the like. It may also be desirable to include isotonic agents such as sugars, sodium chloride, and the like. Prolonged absorption of the injectable pharmaceutical form may be brought about by the inclusion of agents that delay absorption such as aluminum monostearate and gelatin.

In some cases, in order to prolong the effect of the drug, it is desirable to slow the absorption of the drug from subcutaneous or intramuscular injection. This may be accomplished by the use of a liquid suspension of crystalline or amorphous material with poor water solubility. The rate of absorption of the drug then depends upon its rate of dissolution which, in turn, may depend upon crystal size and crystalline form. Alternatively, delayed absorption of a parenterally administered drug form is accomplished by dissolving or suspending the drug in an oil vehicle.

Injectable depot forms are made by forming microencapsule matrices of the drug in biodegradable polymers such as polylactide-polyglycolide. Depending upon the ratio of drug to polymer and the nature of the particular polymer employed, the rate of drug release can be controlled. Examples of other biodegradable polymers include poly(orthoesters) and poly(anhydrides). Depot injectable formulations are also prepared by entrapping the drug in liposomes or microemulsions which are compatible with body tissues.

The injectable formulations can be sterilized, for example, by filtration through a bacterial-retaining filter, or by incorporating sterilizing agents in the form of sterile solid compositions which can be dissolved or dispersed in sterile water or other sterile injectable medium just prior to use.

Solid dosage forms for oral administration include capsules, tablets, pills, powders, and granules. In such solid dosage forms, the active compound is mixed with at least one inert, pharmaceutically acceptable excipient or carrier such as sodium citrate or dicalcium phosphate and/or a) fillers or extenders such as starches, lactose, sucrose, glucose, mannitol, and silicic acid, b) binders such as, for example, carboxymethylcellulose, alginates, gelatin, polyvinylpyrrolidone, sucrose, and acacia, c) humectants such as glycerol, d) disintegrating agents such as agar-agar, calcium carbonate, potato or tapioca starch, alginic acid, certain silicates, and sodium

carbonate, e) solution retarding agents such as paraffin, f) absorption accelerators such as quaternary ammonium compounds, g) wetting agents such as, for example, cetyl alcohol and glycerol monostearate, h) absorbents such as kaolin and bentonite clay, and i) lubricants such as talc, calcium stearate, magnesium stearate, solid polyethylene glycols, sodium lauryl sulfate, and mixtures thereof. In the case of capsules, tablets and pills, the dosage form may also comprise buffering agents.

Solid compositions of a similar type may also be employed as fillers in soft, semi-solid and hard-filled gelatin capsules or liquid-filled capsules using such excipients as lactose or milk sugar as well as high molecular weight polyethylene glycols and the like.

The solid dosage forms of tablets, dragees, capsules, pills, and granules can be prepared with coatings and shells such as enteric coatings and other coatings well known in the pharmaceutical formulating art. They may optionally contain opacifying agents and can also be of a composition that they release the active ingredient(s) only, or preferentially, in a certain part of the intestinal tract, optionally, in a delayed manner. Examples of embedding compositions that can be used include polymeric substances and waxes. Those embedding compositions containing a drug can be placed on medical devices, such as stents, grafts, catheters, and balloons.

The active compounds can also be in micro-encapsulated form, if appropriate, with one or more of the above-mentioned excipients.

Liquid dosage forms for oral administration include pharmaceutically acceptable emulsions, solutions, suspensions, syrups and elixirs. In addition to the active compounds, the liquid dosage forms may contain inert diluents commonly used in the art such as, for example, water or other solvents, solubilizing agents and emulsifiers such as ethyl alcohol, isopropyl alcohol, ethyl carbonate, ethyl acetate, benzyl alcohol, benzyl benzoate, propylene glycol, 1,3-butylene glycol, dimethyl formamide, oils (in particular, cottonseed, groundnut, corn, germ, olive, castor, and sesame oils), glycerol, tetrahydrofurfuryl alcohol, polyethylene glycols and fatty acid esters of sorbitan, and mixtures thereof.

Besides inert diluents, the oral compositions can also include adjuvants such as wetting agents, emulsifying and suspending agents, sweetening, flavoring, and perfuming agents.

Suspensions, in addition to the active compounds, may contain suspending agents as, for example, ethoxylated isostearyl alcohols, polyoxyethylene sorbitol and sorbitan esters, microcrystalline cellulose, aluminum metahydroxide, bentonite, agar, and tragacanth, and mixtures thereof.

5 Topical administration includes administration to the skin or mucosa, including surfaces of the lung and eye. Compositions for topical administration, including those for inhalation, may be prepared as a dry powder which may be pressurized or non-pressurized. In non-pressurized powder compositions, the active ingredient in finely divided form may be used in admixture with a larger-sized pharmaceutically acceptable inert carrier comprising particles having a size, for example, of up to 100
10 micrometers in diameter. Suitable inert carriers include sugars such as lactose. Desirably, at least 95% by weight of the particles of the active ingredient have an effective particle size in the range of 0.01 to 10 micrometers. Compositions for topical use on the skin also include ointments, creams, lotions, and gels.

15 Alternatively, the composition may be pressurized and contain a compressed gas, such as nitrogen or a liquefied gas propellant. The liquefied propellant medium and indeed the total composition is preferably such that the active ingredient does not dissolve therein to any substantial extent. The pressurized composition may also contain a surface active agent. The surface active agent may be a liquid or solid
20 non-ionic surface active agent or may be a solid anionic surface active agent. It is preferred to use the solid anionic surface active agent in the form of a sodium salt.

A further form of topical administration is to the eye, as for the treatment of immune-mediated conditions of the eye such as autoimmune diseases, allergic or inflammatory conditions, and corneal transplants. The compound of the invention is
25 delivered in a pharmaceutically acceptable ophthalmic vehicle, such that the compound is maintained in contact with the ocular surface for a sufficient time period to allow the compound to penetrate the corneal and internal regions of the eye, as for example the anterior chamber, posterior chamber, vitreous body, aqueous humor, vitreous humor, cornea, iris/ciliary, lens, choroid/retina and sclera. The
30 pharmaceutically acceptable ophthalmic vehicle may, for example, be an ointment, vegetable oil or an encapsulating material.

Compositions for rectal or vaginal administration are preferably suppositories or retention enemas which can be prepared by mixing the compounds of this invention with suitable non-irritating excipients or carriers such as cocoa butter,

polyethylene glycol or a suppository wax which are solid at room temperature but liquid at body temperature and therefore melt in the rectum or vaginal cavity and release the active compound.

Compounds of the present invention can also be administered in the form of liposomes. As is known in the art, liposomes are generally derived from phospholipids or other lipid substances. Liposomes are formed by mono- or multi-lamellar hydrated liquid crystals that are dispersed in an aqueous medium. Any non-toxic, physiologically acceptable and metabolizable lipid capable of forming liposomes can be used. The present compositions in liposome form can contain, in addition to a compound of the present invention, stabilizers, preservatives, excipients, and the like. The preferred lipids are the phospholipids and the phosphatidyl cholines (lecithins), both natural and synthetic. Methods to form liposomes are known in the art. See, for example, Prescott, Ed., Methods in Cell Biology, Volume XIV, Academic Press, New York, N.Y. (1976), p. 33 *et seq.*

Compounds of the present invention may also be coadministered with one or more immunosuppressant agents. The immunosuppressant agents within the scope of this invention include, but are not limited to, IMURAN[®] azathioprine sodium, brequinar sodium, SPANIDIN[®] gusperimus trihydrochloride (also known as deoxyspergualin), mizoribine (also known as bredinin), CELLCEPT[®] mycophenolate mofetil, NEORAL[®] Cyclosporin A (also marketed as different formulation of Cyclosporin A under the trademark SANDIMMUNE[®]), PROGRAF[®] tacrolimus (also known as FK-506), sirolimus and RAPAMUNE[®], leflunomide (also known as HWA-486), glucocorticoids, such as prednisolone and its derivatives, antibody therapies such as orthoclone (OKT3) and Zenapax[®], and antithymocyte globulins, such as thymoglobulins.

Example 3

The purpose of this example was to determine the effects of a rapamycin analog on neointimal formation in porcine coronary arteries containing stents. This example illustrates that the rapamycin analog A-179578, when compounded and delivered from the Biocompatibles Biodiviyzio PC Coronary stent favorably affects neointimal hyperplasia and lumen size in porcine coronary arteries. This finding

suggests that such a combination may be of substantial clinical benefit if properly applied in humans by limiting neointimal hyperplasia.

The agent A-179578 is a rapamycin analog. The study set forth in this example was designed to assess the ability of the rapamycin analog A-179578 to reduce neointimal hyperplasia in a porcine coronary stent model. Efficacy of A-179578 in this model would suggest its clinical potential for the limitation and treatment of coronary restenosis in stents following percutaneous revascularization. The domestic swine was used because this model appears to yield results comparable to other investigations seeking to limit neointimal hyperplasia in human subjects.

The example tested A-179578 eluted from coronary stents placed in juvenile farm pigs, and compared these results with control stents. The control stents had polymer alone covering its struts. This is important, for the polymer itself must not stimulate neointimal hyperplasia to a substantial degree. As the eluted drug disappears, an inflammatory response to the polymer could conceivably result in a late "catch-up phenomenon" where the restenosis process is not stopped, but instead slowed. This phenomenon would result in restenosis at late dates in human subjects.

Stents were implanted in two blood vessels in each pig. Pigs used in this model were generally 2-4 months old and weighed 30-40 Kg. Two coronary stents were thus implanted in each pig by visually assessing a Anormal@ stent:artery ratio of 1.1-1.2.

Beginning on the day of the procedure, pigs were given oral aspirin (325 mg daily) and continued for the remainder of their course. General anesthesia was achieved by means of intramuscular injection followed by intravenous ketamine (30 mg/kg) and xylazine (3 mg/kg). Additional medication at the time of induction included atropine (1 mg) and flocillin (1 g) administered intramuscularly. During the stenting procedure, an intraarterial bolus of 10,000 units of heparin was administered.

Arterial access was obtained by cutdown on the right external carotid and placement of an 8F sheath. After the procedure, the animals were maintained on a normal diet without cholesterol or other special supplementation.

The BiodivYsio stent was used with nominal vessel target size of 3.0 mm. See Figure 2. Two coronary arteries per pig were assigned at random to

deployment of the stents. The stent was either a drug eluting stent (polymer plus drug stent) or a stent coated with a polymer only (polymer only stent). The stents were delivered by means of standard guide catheters and wires. The stent balloons were inflated to appropriate sizes for less than 30 seconds.

5 Each pig had one polymer only stent and one polymer plus drug stent placed in separate coronary arteries, so that each pig would have one stent for drug and one for control.

A sample size of 20 pigs total was chosen to detect a projected difference in neointimal thickness of 0.2 mm with a standard deviation of 0.15 mm, at a power of
10 0.95 and beta 0.02.

Animals were euthanized at 28 days for histopathologic examination and quantification. Following removal of the heart from the perfusion pump system, the left atrial appendage was removed for access to the proximal coronary arteries. Coronary arterial segments with injuries were dissected free of the epicardium.
15 Segments containing lesions was isolated, thereby allowing sufficient tissue to contain uninvolved blood vessel at either end. The foregoing segments, each roughly 2.5 cm in length, were embedded and processed by means of standard plastic embedding techniques. The tissues were subsequently processed and stained with hematoxylin-eosin and elastic-van Gieson techniques.

20 Low and high power light microscopy were used to make length measurements in the plane of microscopic view by means of a calibrated reticle and a digital microscopy system connected to a computer employing calibrated analysis software.

The severity of vessel injury and the neointimal response were measured by
25 calibrated digital microscopy. The importance of the integrity of the internal elastic lamina is well-known to those skilled in the art. A histopathologic injury score in stented blood vessels has been validated as being closely related to neointimal thickness. This score is related to depth of injury and is as follows:

30	<u>Score</u>	<u>Description of Injury</u>
	0	Internal elastic lamina intact; endothelium typically denuded, media compressed but not lacerated.

- 1 Internal elastic lamina lacerated; media typically compressed but not lacerated.
- 2 Internal elastic lacerated; media visibly lacerated; external elastic lamina intact but compressed.
- 3 External elastic lamina lacerated; typically large lacerations of media extending through the external elastic lamina; coil wires sometimes residing in adventitia.

This quantitative measurement of injury was assessed for all stent wires of each stent section. The calibrated digital image was also used to measure at each stent wire site the neointimal thickness. Lumen area, area contained with the internal elastic lamina, and area within the external elastic lamina were also measured.

At each stent wire site for a given section, the neointimal thickness was averaged to obtain a mean injury score for each section. The measurement of neointimal thickness was made to the abluminal side of the stent wire, because the neointimal in all cases includes this thickness.

The mid-stent segment was used for measurement, analysis, and comparison. Data were also recorded (and included in the data section of this report) for proximal and distal segments.

The data analysis methods for this study did not need to take into account variable arterial injury across treatment/control groups, because mild to moderate injury is sensitive enough to detect treatment differences. Paired t-testing was performed to compare variables across the polymer only stents (control group) and polymer plus drug stents (treatment group). No animal died in this study before scheduled timepoints.

Table 3 shows the pigs and arteries used. In Table 3, LCX means the circumflex branch of the left coronary artery, LAD means the left anterior descending coronary artery, and RCA means the right coronary artery.

Table 3

Pigs and Vessels Used

1	2000-G-693	RCA - Control
	2000-G-693	LCX - Test
2	2000-G-698	RCA - Test
	2000-G-698	LAD - Control
3	2000-G-702	RCA - Test
	2000-G-702	LAD - Control
4	2000-G-709	RCA - Control
	2000-G-709	LAD - Test
5	2000-G-306	RCA - Control
	2000-G-306	LAD - Test
	2000-G-306	* LCX - Test
6	2000-G-672	RCA - Test
	2000-G-672	LAD - Control
7	2000-G-712	RCA - Control
	2000-G-712	LCX - Test
8	2000-G-735	RCA - Control
	2000-G-735	LAD - Test
9	2000-G-736	RCA - Control
	2000-G-736	LCX - Test
10	2000-G-740	RCA - Test
	2000-G-740	LAD - Control
11	2000-G-742	LAD - Test
	2000-G-742	OM (LCX) - Control
12	2000-G-744	RCA - Test
	2000-G-744	LAD - Control
13	2000-G-748	RCA - Test
	2000-G-748	LAD - Control
14	2000-G-749	RCA - Control
	2000-G-749	LCX - Test
15	2000-G-753	RCA - Control
	2000-G-753	LAD - Test
16	2000-G-754	RCA - Test
	2000-G-754	LCX -Control
17	2000-G-755	RCA - Control
	2000-G-755	LAD - Test
18	2000-G-756	RCA - Test
	2000-G-756	LAD - Control
19	2000-G-757	LAD - Control
	2000-G-757	LCX - Test
20	2000-G-760	LAD - Test
	2000-G-760	LCX -Control

5

Table 4 shows the summary results for all data for mean injury and neointimal thickness for each stent, including proximal, mid, and distal segments. Table 4 also

shows lumen size, percent stenosis, and artery size as measured by the internal elastic laminae (IEL) and external elastic laminae (EEL).

Table 4

Summary: All Measures (Distal, Mid, Proximal)

ID	prox ref	dist ref	lumen	IEL	EEL	mean injury	% stenosis	Neointimal area	NIT
Control	Distal								
Mean	4.46	3.96	4.88	7.66	9.00	0.22	36.10	2.79	0.41
SD	1.20	1.16	1.30	1.15	1.10	0.26	15.41	1.29	0.17
Control	Mid								
Mean	4.46	3.96	4.94	7.71	9.08	0.08	36.23	2.77	0.38
SD	1.20	1.16	1.44	1.07	1.15	0.14	14.93	1.20	0.16
Control	Proximal								
Mean	4.46	3.96	5.11	7.89	9.30	0.15	35.35	2.78	0.38
SD	1.20	1.16	1.38	1.33	1.42	0.22	11.94	1.04	0.12
Test	Distal								
Mean	4.26	3.41	6.04	7.70	9.01	0.26	22.35	1.66	0.25
SD	1.26	0.96	1.55	1.49	1.47	0.43	8.58	0.58	0.06
Test	Mid								
Mean	4.26	3.41	6.35	7.75	8.98	0.04	18.71	1.41	0.22
SD	1.26	0.96	1.29	1.18	1.31	0.07	5.68	0.33	0.05
Test	Proximal								
Mean	2.56	2.15	3.31	4.06	4.66	0.19	16.79	1.29	0.18
SD	1.66	1.37	2.39	3.48	4.15	0.13	9.97	0.80	0.12

There was no statistically significant difference for neointimal area or thickness across proximal, mid, or distal segments within the test group (polymer plus drug stents) or control groups (polymer only stents). This observation is quite consistent with prior studies, and thus allows use of only the mid segment for statistical comparison of test devices (polymer plus drug stents) vs. control devices (polymer only stents).

Table 5 shows the statistical t-test comparisons across test groups and control groups. There was a statistically significant difference in neointimal thickness, neointimal area, lumen size, and percent lumen stenosis, the drug eluting stent being clearly favored. Conversely, there were no statistically significant differences between

the test group (polymer plus drug stents) and the control group (polymer only stents) for mean injury score, external elastic laminae, or internal elastic laminae areas.

Table 5

Statistical Comparison of Test vs. Control Parameters: Mid-Section Data

t-test Statistics							
Parameter	Difference	t-test	DF	Std Error	Lower 95%	Upper 95%	p
Lumen	-1.17	-2.28	38	0.52	-2.21	-0.13	0.029
IEL	0.03	0.088	38	0.36	-0.71	0.78	0.93
EEL	0.2	0.499	38	0.39	-0.599	0.99	0.62
NI Thickness	0.18	5.153	38	0.034	0.106	0.244	<.0001
NI Area	1.21	3.62	38	0.33	0.53	1.88	0.0008
Mean Injury	0.038	1.137	38	0.033	-0.02	0.106	0.26
% Stenosis	14.54	2.97	38	4.9	4.61	24.47	0.005

The reference arteries proximal and distal to the stented segments were observed, and quantitated. These vessels appeared normal in all cases, uninjured in both the control group (polymer only stents) and the test group (polymer plus drug stents). See Figures 3A and 3B. The data below show there were no statistically significant differences in size between the stents in the control group and the stents in the test group.

Proximal Reference
Diameter (mm)

Distal Reference
Diameter (mm)

Control

(mean \pm SD)

4.46 \pm 1.20

3.96 \pm 1.16

Test

(mean \pm SD)

4.26 \pm 1.26

3.41 \pm 0.96

The data suggest that statistically significant differences exist, and these differences favor the stent that elutes A-179578. The stent of this invention results in lower neointimal area, lower neointimal thickness, and greater lumen area. There were no significant differences within the test group (polymer plus drug stents) and the control group (polymer only stents) for neointimal or injury parameters. There were no significant differences in artery sizes (including the stent) for the control group compared to the test group. These latter findings suggest no significant difference in the arterial remodeling characteristics of the polymeric coating containing the drug.

At most, mild inflammation was found on both the polymer plus drug stent and the polymer only stent. This finding suggests that the polymer exhibits satisfactory biocompatibility, even without drug loading. Other studies show that when drug has completely gone from the polymer, the polymer itself creates enough inflammation to cause neointima. This phenomenon may be responsible for the late Acatch-up@ phenomenon of clinical late restenosis. Because the polymer in this example did not cause inflammation in the coronary arteries, late problems related to the polymer after the drug is exhausted are unlikely.

In conclusion, a stent containing the compound A-179578 with a polymer showed a reduction in neointimal hyperplasia in the porcine model when placed in a coronary artery.

Example 4

The purpose of this example is to determine the rate of release of the A-179578 drug from 316L Electropolished Stainless Steel Coupons coated with a biocompatible polymer containing phosphorylcholine side groups.

Rubber septa from lids from HPLC vials were removed from the vials and placed into glass vials so that the "Teflon" side faced up. These septa served as supports for the test samples. The test samples were 316L stainless steel coupons that had been previously coated with a biocompatible polymer containing phosphorylcholine side groups (PC polymer). Coronary stents are commonly made of 316L stainless steel and can be coated with the PC polymer to provide a depot site for loading drugs. The coated coupons, which serve to simulate stents, were placed onto the septa. By using a glass Hamilton Syringe, a solution of A-179578

and ethanol (10 μ l) was applied to the surface of each coupon. The solution contained A-179578 (30.6 mg) dissolved in 100% ethanol (3.0 ml). The syringe was cleaned with ethanol between each application. The cap to the glass vial was placed on the vial loosely, thereby assuring proper ventilation. The coupon was allowed to
5 dry for a minimum of 1.5 hours. Twelve (12) coupons were loaded in this way - six being used to determine the average amount of drug loaded onto the device and six being used to measure the time needed to release the drug from the devices.

To determine the total amount of A-179578 loaded onto a coupon, a coupon was removed from the vial and placed into 50/50 acetonitrile/ 0.01M phosphate
10 buffer (pH 6.0, 5.0 ml). The coupon was placed onto a 5210 Branson sonicator for one hour. The coupon was then removed from the solution, and the solution was assayed by HPLC.

The time release studies were performed by immersing and removing the individual coupons from fresh aliquots (10.0 ml) of 0.01 M phosphate buffer at a pH
15 of 6.0 at each of the following time intervals - 5, 15, 30 and 60 minutes. For the remaining time points of 120, 180, 240, 300, 360 minutes, volumes of 5.0 ml of buffer were used. To facilitate mixing during the drug release phase, the samples were placed onto an Eberbach shaker set at low speed. All solution aliquots were assayed by HPLC after the testing of the last sample was completed.

20 The HPLC analysis was performed with a Hewlett Packard series 1100 instrument having the following settings:

Injection Volume	=	100 μ l
Acquisition Time	=	40 minutes
25 Flow Rate	=	1.0 ml/min
Column Temperature	=	40 $^{\circ}$ C
Wavelength	=	278 nm
Mobile Phase	=	65% Acetonitrile/35% H ₂ O
Column	=	YMC ODS-A S5 μ m,4.6 x 250mm Part No.
30		A12052546WT

The results from the above experiment showed the following release data:

Table 6

Time (min.)	Percent Release	Standard Deviation
0.00	0.00	0.00
5.00	1.87	1.12
15.00	2.97	1.47
30.00	3.24	1.28
60.00	3.29	1.29
120.00	3.92	1.28
180.00	4.36	1.33
240.00	4.37	1.35
300.00	6.34	2.07
360.00	7.88	1.01

5

Example 5

10 The purpose of this example was to determine the loading and release of A-179578 from 15mm BiodivYsio drug delivery stents.

15 To load the stents with drug, a solution of A-179578 in ethanol at a concentration of 50 mg/ml was prepared and dispensed into twelve vials. Twelve individual polymer-coated stents were placed on fixtures designed to hold the stent in a vertical position and the stents were immersed vertically in the drug solution for five minutes. The stents and fixtures were removed from the vials and excess drug solution was blotted away by contacting the stents with an absorbent material. The stents were then allowed to dry in air for 30 minutes in an inverted vertical position.

20 The stents were removed from the fixtures, and each stent was placed into 50/50 acetonitrile/phosphate buffer (pH 5.1, 2.0 ml) and sonicated for one hour. The stents were removed from the solution and solutions were assayed for concentration of drug, which allowed calculation of the amount of drug originally on the stents. This method was independently shown to remove at least 95% of the drug from the stent coating. On average, the stents contained 60 micrograms of drug \pm 20 micrograms.

25

 The drug-loaded stents were placed on the fixtures and placed into 0.01 M phosphate buffer (pH = 6.0, 1.9 ml) in individual vials. These samples were placed

onto a Eberbach shaker set at low speed to provide back-and-forth agitation. To avoid approaching drug saturation in the buffer, the stents were transferred periodically to fresh buffer vials at the following points: 15, 30, 45, 60, 120, 135, 150, 165, 180, 240, 390 minutes. The dissolution buffer vials were assayed by HPLC for the drug concentration at the end of the drug release period studied. The data, represented as % cumulative release of the drug as a function of time, is shown in tabular form below:

Table 7

Time (min)	% Cumulative Release of Drug
15	0.3
30	1.1
45	2.1
60	3.2
120	4.3
135	5.9
150	6.3
165	6.8
180	7.4
240	10.8
390	13.2

Example 6

The purpose of this example was to evaluate the safety and efficacy of different drug dosages on neointima formation. Drug was delivered from the BiodivYsio OC stent (15mm) coated with A-179578. In-stent neointima formation was measured at four time intervals - 3 days, 1 month, and 3 months - in the coronary arteries of adult miniature swine. Forty (40) animals were studied at each time interval (10 animals per dose). Each animal received one drug-coated stent and one control stent. The control stent contained no drug. Table 8 shows the dosing scheme for swine efficacy study.

Table 8

	Dose group 1 (μg)	Dose group 2 (μg)	Dose group 3 (μg)	Dose group 4 (μg)
A-179578 per stent	15	45	150	400
A-179578 per mm of stent	1	3	10	27

5 Potential local tissue toxicity was assessed at all time intervals by examining histopathologic changes in the stented region, adjacent coronary segments, perivascular tissue, and subserved myocardium. The mortality, angiographic implant and restudy data, histomorphometry data, and stent site histopathology were studied

10 Three-Day Group

Histopathology in combination with scanning electron microscopy provided information regarding the short-term response to the implanted stent. The responses were similar in the control group and all dose groups, and the responses
 15 involved compression of the tunica media without remarkable necrosis, an accumulation of thrombus and inflammatory cells mostly localized to the stent struts, and early evidence of endothelial recovery and smooth muscle cell invasion of the thin mural thrombi. There were no extensive thrombi or remarkable intramural hemorrhages. The adventitia in some samples displayed either focal or diffuse
 20 inflammatory infiltrates, and occasionally, there was plugging or congestion of the vasa vasora. There was no evidence of medial necrosis in any sample.

Scanning electron microscopy showed similar appearance of the luminal surface three days after the implant of the coronary stent in all dose groups. The shape of the stent was clearly embedded in a thin layer of tissue. The endothelium
 25 was intact between the struts and even over the struts; a confluent or nearly confluent layer of endothelial-like cells had covered the luminal surface. There were scattered adherent platelets, platelet microthrombi, and leukocytes over the stents and on the intact remnant endothelium in the inter-strut spaces. In arteries with more severe stent-induced vessel damage, there were more substantial mural

thrombi, but the extent of endothelial recovery over the stent struts did not appear retarded, regardless of the dosage of A-179578.

One-Month Group

5

The histomorphometry data for the one-month series indicated a significant inhibitory effect of locally eluted A-179578 on neointima formation in stented coronary arteries of swine. Intima area normalized to injury score was significantly decreased for dose groups 3 and 4 (10 and 27 µg/mm) as compared with the control; there were also trends for decreases in absolute intima area and intima thickness for both dose groups 3 and 4 as compared with the control, and a tendency towards decreased histologic % stenosis for dose group 3 as compared with the control.

The control stents displayed morphology typical of stents implanted in coronary arteries of Yucatan miniature swine at one month. The tunica media was compressed or thinned without necrosis subjacent to profiles of stent struts; there were only occasional inflammatory infiltrates; and the neointima ranged in size from relatively thin to moderately thin, and were composed of spindle-shaped and stellate cells in an abundant extracellular matrix, with only rare small foci of fibrinoid material around the profiles of the stent struts. The drug-coated stents showed similar compression of the tunica media without any substantial necrosis at any dose; like control devices, there was little inflammation present. The neointima was notably thinner in dose groups 3 and 4, in some cases being composed of only a few layers of cells. In all dose groups, there were substantial numbers of samples in which moderately sized fibrinoid deposits and inspissated thrombi were observed in the deep neointima. These were usually associated with the stent struts but sometimes extended between strut profiles. However, in no case was there exposure of thrombus on the luminal surface, as the deposits were encapsulated within fibrocellular tissue and covered with a flattened layer of periluminal endothelial-like cells.

Scanning electron microscopy confirmed that a confluent layer of endothelial or endothelial-like cells covered the entire stented surface, and there was no difference between drug-coated stents and control stents in terms of adherence of blood elements; leukocytes were present in approximately equal numbers in all groups. These findings demonstrate that while A-179578 was associated with

decreased neointima formation and persistent mural thrombi, sufficient vessel wall healing in response to stent injury had occurred within one month after the stent had been implanted. This vessel wall healing had rendered the luminal surface non-reactive for platelet adhesion and thrombus formation, and minimally reactive for leukocyte adherence. Additionally, there was no evidence of vessel wall toxicity even at the highest dose (27 μ g/mm), as there was no medial necrosis or stent malapposition.

Three-Month Group

There were no significant differences between the dose groups for any histomorphometric parameters of stented coronary arterial dimension in the three-month period of the study. However, there were weak trends for decreases in the two primary variables describing neointima formation - the cross-sectional area and the % area stenosis of the lumen.

The histopathologic appearance of the control stents in the swine coronary artery samples at three months after the implant appeared similar to that of the controls from the one-month group, and similar to those of all the groups in the three-month period. All samples showed fibrocellular neointima formation with mostly spindle-shaped smooth muscle-like cells in the neointima and a confluent squamous periluminal cell layer. There were no intramural hemorrhages or persistent fibrinoid deposits in the neointima; however some samples, particularly those with thicker neointima, showed evidence of prior thrombus accumulation and subsequent organization in the form of neovascularization in the neointima. On occasion, samples showed evidence of moderate to severe inflammatory reactions localized to the stent struts, associated with destruction of the tunica media architecture. These were most often associated with thicker neointima as well. However, these were few in number and were found in the control group as well as in the drug-coated stent groups. It is presumed that these represented either animal-specific generalized reactions to the implanted stent, evidence of contamination of the stent, or some combination of these two factors, and is commonly found at an incidence of about 10-15% in the studies of stent implants in swine coronary arteries. There was no evidence of necrosis of the tunica media or separation of the media from the stent in any sample. The adventitia of most three-month implants appeared to have

somewhat greater neovascularization than did the one-month implants, but this did not appear related to control or test stent group. Scanning electron microscopy demonstrated confluent endothelium with rare adherent blood cells in the control group and all dose groups.

5

Conclusions

The stent coated with A-179578 reduced in-stent neointima formation in swine coronary arteries and provided clear evidence of a biologic drug effect (unresorbed thrombus/fibrin deposits of neointima) at one month. There was a weak tendency for the stent coated with A-179578 to show a persistent inhibitory effect at the longer-term time interval of three months. There was no local coronary arterial wall toxicity in the form of medial necrosis or stent malapposition associated with any dose group, including the highest dose of approximately 27 µg/mm stent length at any time interval examined. All stents were well incorporated into the tissue, and there was evidence of stable healing responses in the form of fibrocellular neointimal incorporation and endothelial coverage at the one-month interval and at the three-month interval. The trend towards a sustained inhibitory effect at three months after the stent was implanted in this animal is surprising and provides evidence for potentially persistent effects in preventing clinical restenosis resulting from implanted stents.


It is understood that the foregoing detailed description and accompanying examples are merely illustrative and are not to be taken as limitations upon the scope of the invention, which is defined solely by the appended claims and their equivalents. Various changes and modifications to the disclosed embodiments will be apparent to those skilled in the art. Such changes and modifications, including without limitation those relating to the chemical structures, substituents, derivatives, intermediates, syntheses, formulations and/or methods of use of the invention, may be made without departing from the spirit and scope thereof.

30

WHAT IS CLAIMED IS:

1. A medical device comprising a supporting structure and the therapeutic substance

5



or a pharmaceutically acceptable salt or prodrug thereof and at least one other therapeutic substance selected from the group consisting of anti-proliferative agents, anti-platelet agents, anti-inflammatory agents, anti-thrombotic agents, thrombolytic agents, cytotoxic drugs, agents that inhibit cytokine or chemokine binding, cell de-differentiation inhibitors, anti-lipaedemic agents, matrix metalloproteinase inhibitors, and cytostatic drugs.

2. The medical device of claim 1, wherein said anti-proliferative agent is an anti-mitotic agent.

3. The medical device of claim 2, wherein said anti-mitotic agent is selected from the group consisting of vinca alkaloids, anti-mitotic alkylating agents, and anti-mitotic metabolites.

4. The medical device of claim 1, wherein said anti-platelet agent is selected from the group consisting of agents that inhibit adhesion of platelets, agents that inhibit aggregation of platelets, and agents that inhibit activation of platelets.

25

5. The medical device of claim 1, wherein said anti-inflammatory agent is estradiol.


6. The medical device of claim 1, wherein said anti-inflammatory agent is
5 dexamethasone.

7. The medical device of claim 1, wherein said supporting structure is selected from the group consisting of coronary stents, peripheral stents, catheters, arterio-venous grafts, by-pass grafts, and drug delivery balloons used in the
10 vasculature.

8. The medical device of claim 1, wherein said supporting structure further comprises a coating, said coating containing said therapeutic substances.

15 9. The medical device of claim 8, wherein said coating is polymeric.


10. The medical device of claim 1, wherein said therapeutic substance is



20


or a pharmaceutically acceptable salt or prodrug thereof.

11. The medical device of claim 1, wherein said therapeutic substance is



or a pharmaceutically acceptable salt or prodrug thereof.

- 5 12. A medical device comprising a supporting structure and the therapeutic substance



- 10 or a pharmaceutically acceptable salt or prodrug thereof and at least one other therapeutic substance.

13. The medical device of claim 12, wherein said at least one other therapeutic substance is a drug selected from the group consisting of anti-proliferative agents, anti-platelet agents, anti-inflammatory agents, anti-thrombotic agents, thrombolytic agents, cytotoxic drugs, agents that inhibit cytokine or
- 15

chemokine binding, cell de-differentiation inhibitors, anti-lipaedemic agents, matrix metalloproteinase inhibitors, and cytostatic drugs.

14. The medical device of claim 13, wherein said anti-inflammatory agent
5 is selected from the group consisting of estradiol and dexamethasone.


15. The medical device of claim 12, wherein said anti-lipaedemic agent is fenofibrate and said matrix metalloproteinase inhibitor is batimistat.

10 16. The medical device of claim 12, wherein said supporting structure further comprises a coating, said coating containing said therapeutic substances.

17. The medical device of claim 12, wherein said supporting structure is selected from the group consisting of coronary stents, peripheral stents, catheters,
15 arterio-venous grafts, by-pass grafts, and drug delivery balloons used in the vasculature.

18. A medical device comprising a supporting structure having a coating on the surface thereof, said coating containing the therapeutic substance

20



or a pharmaceutically acceptable salt or prodrug thereof and at least one drug selected from the group consisting of anti-proliferative agents, anti-platelet agents,
25 anti-inflammatory agents, anti-thrombotic agents, thrombolytic agents, cytotoxic drugs, agents that inhibit cytokine or chemokine binding, cell de-differentiation

inhibitors, anti-lipaedemic agents, matrix metalloproteinase inhibitors, and cytostatic drugs.

19. The medical device of claim 18, wherein said anti-proliferative agent is
5 an anti-mitotic agent.

20. The medical device of claim 19, wherein said anti-mitotic agent is
selected from the group consisting of vinca alkaloids, anti-mitotic alkylating agents,
and anti-mitotic metabolites.

10

21. The medical device of claim 18, wherein said anti-platelet agent is
selected from the group consisting of agents that inhibit adhesion of platelets, agents
that inhibit aggregation of platelets, and agents that inhibit activation of platelets.

22. The medical device of claim 18, wherein said anti-inflammatory agent
15 is estradiol.

23. The medical device of claim 18, wherein said anti-inflammatory agent
is dexamethasone.

20

24. The medical device of claim 18, wherein said supporting structure is
selected from the group consisting of coronary stents, peripheral stents, catheters,
arterio-venous grafts, by-pass grafts, and drug delivery balloons used in the
vasculature.

25


25. The medical device of claim 18, wherein said coating is polymeric.

26. The medical device of claim 25, wherein said polymeric coating is
biostable.

30

27. The medical device of claim 25, wherein said polymeric coating is
biodegradable.


28. The medical device of claim 18, wherein said therapeutic substance is



or a pharmaceutically acceptable salt or prodrug thereof.


5

29. The medical device of claim 18, wherein said therapeutic substance is



10 or a pharmaceutically acceptable salt or prodrug thereof.

30. A medical device comprising a supporting structure having a coating on the surface thereof, said coating containing the therapeutic substance



or a pharmaceutically acceptable salt or prodrug thereof and at least one drug selected from the group consisting of anti-proliferative agents, anti-platelet agents, anti-inflammatory agents, anti-thrombotic agents, thrombolytic agents, cytotoxic drugs, agents that inhibit cytokine or chemokine binding, cell de-differentiation inhibitors, anti-lipaedemic agents, matrix metalloproteinase inhibitors, and cytostatic drugs.

31. The medical device of claim 30, wherein said anti-proliferative agent is an anti-mitotic agent.

32. The medical device of claim 31, wherein said anti-mitotic agent is selected from the group consisting of vinca alkaloids, anti-mitotic alkylating agents, and anti-mitotic metabolites.

33. The medical device of claim 30, wherein said anti-platelet agent is selected from the group consisting of agents that inhibit adhesion of platelets, agents that inhibit aggregation of platelets, and agents that inhibit activation of platelets.

34. The medical device of claim 30, wherein said anti-inflammatory agent is estradiol.

35. The medical device of claim 30, wherein said anti-inflammatory agent is dexamethasone.


36. The medical device of claim 30, wherein said supporting structure is selected from the group consisting of coronary stents, peripheral stents, catheters, arterio-venous grafts, by-pass grafts, and drug delivery balloons used in the vasculature.

37. The medical device of claim 30, wherein said coating is polymeric.

38. The medical device of claim 37, wherein said polymeric coating is biostable.

39. The medical device of claim 37, wherein said polymeric coating is biodegradable.

40. A medical device comprising a supporting structure capable of containing or supporting a pharmaceutically acceptable carrier or excipient, said carrier or excipient containing the therapeutic substance



or a pharmaceutically acceptable salt or prodrug thereof and at least one other therapeutic substance selected from the group consisting of anti-proliferative agents, anti-platelet agents, anti-inflammatory agents, anti-thrombotic agents, thrombolytic agents, cytotoxic drugs, agents that inhibit cytokine or chemokine binding, cell de-

differentiation inhibitors, anti-lipaemic agents, matrix metalloproteinase inhibitors, and cytostatic drugs.

5 41. The medical device of claim 40, wherein said anti-proliferative agent is an anti-mitotic agent.

10 42. The medical device of claim 41, wherein said anti-mitotic agent is selected from the group consisting of vinca alkaloids, anti-mitotic alkylating agents, and anti-mitotic metabolites.

 43. The medical device of claim 40, wherein said anti-platelet agent is selected from the group consisting of agents that inhibit adhesion of platelets, agents that inhibit aggregation of platelets, and agents that inhibit activation of platelets.

15 44. The medical device of claim 40, wherein said anti-inflammatory agent is estradiol.

 45. The medical device of claim 40, wherein said anti-inflammatory agent is dexamethasone.

20 46. The medical device of claim 40, wherein said supporting structure includes a framework in the form of a stent.

25 47. The medical device of claim 40, wherein said supporting structure is selected from the group consisting of coronary stents, peripheral stents, catheters, arterio-venous grafts, by-pass grafts, and drug delivery balloons used in the vasculature.

30 48. The medical device of claim 40, wherein said supporting structure further comprises a coating, said coating containing said therapeutic substances.

 49. The medical device of claim 48, wherein said coating is polymeric.

50. The medical device of claim 49, wherein said polymeric coating is biostable.

5 51. The medical device of claim 49, wherein said polymeric coating is biodegradable.

52. The medical device of claim 40, wherein said supporting structure includes a polymeric framework containing said therapeutic substances.

10 53. The medical device of claim 40, wherein said polymeric framework is biodegradable.

54. The medical device of claim 40, wherein said anti-lipaedemic agent is fenofibrate.
15

55. The medical device of claim 40, wherein said matrix metalloproteinase inhibitor is batimistat.

20

1/2




FIG.1

2/2

The BiodivYsio PC-coated Stent




FIG.2

Polymer Only




FIG.3A

Polymer plus Drug



FIG.3B

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
20 March 2003 (20.03.2003)

PCT

(10) International Publication Number
WO 2003/022807 A3

(51) International Patent Classification:

A61L 31/16 (2006.01) A61L 27/54 (2006.01)

(21) International Application Number:

PCT/US2002/028776

(22) International Filing Date:

10 September 2002 (10.09.2002)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

09/950,307	10 September 2001 (10.09.2001)	US
10/235,572	6 September 2002 (06.09.2002)	US

(71) Applicant (for all designated States except US): **ABBOTT LABORATORIES** [US/US]; D-377 AP6A-1, 100 Abbott Park Road, Abbott Park, IL 60064-6008 (US).

(72) Inventors; and



(75) Inventors/Applicants (for US only): **MOLLISON, Karl, W.** [US/US]; 4020 N Harvard Ave, Arlington Heights, IL 60004 (US). **LECAPTAIN, Angela, M.** [US/US]; 555Bridlewood Ln, Oak Creek, WI 53154 (US). **BURKE, Sandra, E.** [US/US]; 1025 Regency Lane, Libertyville, IL 60048 (US). **CROMACK, Keith, R.** [US/US]; 18066 W Banbury Dr, Gurnee, IL 60031 (US). **TARCHA, Peter, J.** [US/US]; 21651 Gelden Road, Lake Villa, IL 60046 (US). **CHEN, Yen-Chih, J.** [US/US]; 3315 Dartmouth Place, Evanston, IL 60201 (US).(74) Agents: **WEINSTEIN, David, L.** et al.; D-377 AP6A-1, 100 Abbott Park Road, Abbott Park, IL 60064-6008 (US).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ,

[Continued on next page]

(54) Title: MEDICAL DEVICES CONTAINING RAPAMYCIN ANALOGS



(I)

(57) Abstract: A medical device comprising a supporting structure capable of containing or supporting a pharmaceutically acceptable carrier or excipient, which carrier or excipient may contain one or more therapeutic agents or substances, with the carrier preferably including a coating on the surface thereof, and the coating containing the therapeutic substances, such as, for example, drugs. Supporting structures for the medical devices that are suitable for use in this invention include, but are not limited to, coronary stents, peripheral stents, catheters, arterio-venous grafts, by-pass grafts, and drug delivery balloons used in the vasculature. Drugs that are suitable for use in this invention include, but are not limited to Formula (I). This drug can be used in combination with another drug including those selected from anti-proliferative agents, anti-platelet agents, anti-inflammatory agents, anti-thrombotic agents, cytotoxic drugs, agents that inhibit cytokine or chemokine binding, cell de-differentiation inhibitors, anti-lipademic agents, matrix metalloproteinase inhibitors, cytostatic drugs, or combinations of these drugs.



TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- *with international search report*
- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

(88) Date of publication of the international search report:
14 June 2007

(15) Information about Correction:**Previous Correction:**

see PCT Gazette No. 50/2003 of 11 December 2003

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US2002/028776

A. CLASSIFICATION OF SUBJECT MATTER
INV. A61L31/16 A61L27/54

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
A61L A61K A61F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6 273 913 B1 (KING KRISTEN ET AL) 14 August 2001 (2001-08-14) column 4, lines 64-66 column 5, lines 21-24 column 5, line 65 - column 6, line 45	1-55
A	US 6 015 815 A (MOLLISON KARL W) 18 January 2000 (2000-01-18) abstract; examples column 8, lines 51-66 column 10, lines 47-64 column 11, lines 5-12, 47-62 column 12, lines 13-41	1-55
X, P	EP 1 236 478 A (MEDTRONIC AVE INC) 4 September 2002 (2002-09-04) claim 25	1-55
	----- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

19 April 2007

Date of mailing of the international search report

20. 04. 2007

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Böhm, Ingo

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US2002/028776

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X,P	WO 01/87372 A (CORDIS CORP) 22 November 2001 (2001-11-22) page 5, lines 9-26 page 7, lines 13-30 claims	1-11, 18-29
A,P	----- WO 02/066092 A (BOURGUIGNON BERNARD ;LAWRENCE MARCUS F (CA); ANGIOGENE INC (CA); L) 29 August 2002 (2002-08-29) page 3, line 15 - page 8, line 3 claims 8,29 -----	1-11, 18-29

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US2002/028776

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6273913	B1	14-08-2001	US 2001027340 A1	04-10-2001
US 6015815	A	18-01-2000	US 6329386 B1	11-12-2001
EP 1236478	A	04-09-2002	AT 307622 T	15-11-2005
			DE 60206819 D1	01-12-2005
			DE 60206819 T2	27-07-2006
WO 0187372	A	22-11-2001	AT 298592 T	15-07-2005
			AU 6158101 A	26-11-2001
			AU 6295701 A	26-11-2001
			CA 2408606 A1	22-11-2001
			DE 60111743 D1	04-08-2005
			DE 60111743 T2	15-12-2005
			EP 1289576 A1	12-03-2003
			ES 2244622 T3	16-12-2005
			JP 2003533493 T	11-11-2003
			MX PA02011099 A	19-08-2004
			MX PA02011186 A	09-09-2004
			PT 1289576 T	31-10-2005
WO 02066092	A	29-08-2002	NONE	

CORRECTED VERSION

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
20 March 2003 (20.03.2003)

PCT

(10) International Publication Number
WO 03/022807 A2(51) International Patent Classification⁷: C07D

(21) International Application Number: PCT/US02/28776

(22) International Filing Date:
10 September 2002 (10.09.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/950,307 10 September 2001 (10.09.2001) US
10/235,572 6 September 2002 (06.09.2002) US(71) Applicant (for all designated States except US): **ABBOTT LABORATORIES** [US/US]; D-377 AP6A-1, 100 Abbott Park Road, Abbott Park, IL 60064-6008 (US).


(72) Inventors; and

(75) Inventors/Applicants (for US only): **MOLLISON, Karl, W.** [US/US]; 4020 N Harvard Ave, Arlington Heights, IL 60004 (US). **LECAPTAIN, Angela, M.** [US/US]; 555 Bridlewood Ln, Oak Creek, WI 53154 (US). **BURKE, Sandra, E.** [US/US]; 1025 Regency Lane, Libertyville, IL 60048 (US). **CROMACK, Keith, R.** [US/US]; 18066 W Banbury Dr, Gurnee, IL 60031 (US). **TARCHA, Peter, J.** [US/US]; 21651 Gelden Road, Lake Villa, IL 60046 (US). **CHEN, Yen-Chih, J.** [US/US]; 3315 Dartmouth Place, Evanston, IL 60201 (US).(74) Agents: **WEINSTEIN, David, L.** et al.; D-377 AP6A-1, 100 Abbott Park Road, Abbott Park, IL 60064-6008 (US).


(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,

[Continued on next page]

(54) Title: MEDICAL DEVICES CONTAINING RAPAMYCIN ANALOGS



(57) Abstract: A medical device comprising a supporting structure capable of containing or supporting a pharmaceutically acceptable carrier or excipient, which carrier or excipient may contain one or more therapeutic agents or substances, with the carrier preferably including a coating on the surface thereof, and the coating containing the therapeutic substances, such as, for example, drugs. Supporting structures for the medical devices that are suitable for use in this invention include, but are not limited to, coronary stents, peripheral stents, catheters, arterio-venous grafts, by-pass grafts, and drug delivery balloons used in the vasculature. Drugs that are suitable for use in this invention include, but are not limited to Formula (I). This drug can be used in combination with another drug including those selected from anti-proliferative agents, anti-platelet agents, anti-inflammatory agents, anti-thrombotic agents, cytotoxic drugs, agents that inhibit cytokine or chemokine binding, cell de-differentiation inhibitors, anti-lipaedemic agents, matrix metalloproteinase inhibitors, cytostatic drugs, or combinations of these drugs.



(I)



GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— *without international search report and to be republished upon receipt of that report*

(48) Date of publication of this corrected version:

11 December 2003

(15) Information about Correction:

see PCT Gazette No. 50/2003 of 11 December 2003, Section II

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.